

Unipren® A3 CRLA010 55A FD XP03 UP372

Grupo Petropol Polímeros

TPE

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	55	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	890	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2	h	-
Melt temperature	170 - 200	°C	-
Mold temperature	30 - 60	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, South and Central America

Delivery form

Natural Color