

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	2	MPa	ASTM D 412
Modulus at 300% Elongation	3	MPa	ASTM D 412
Shore A Hardness	65	-	ASTM D 2240
Tear Strength	40	kN/m	ASTM D 624
Tensile Strength	7	MPa	ASTM D 412
Other Standards^{S1}			
Elongation at Yield	600	%	ASTM D 412

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	980	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2	h	-
Melt temperature	180 - 200	°C	-
Mold temperature	40	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Features

Good Adhesion

Delivery form

Natural Color

Regional Availability

North America, Europe, South and Central America