

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	5	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Shore A Hardness	45	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2	h	-
Melt temperature	170 - 200	°C	-
Mold temperature	25 - 50	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, South and Central America

Delivery form

Black