

Volaprint TPE 94

TPE

Volaprint 3 de-store

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	5	MPa	ISO 527
Charpy notched impact strength, +23°C	17	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, A	61	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
Density	930	kg/m ³	ISO 1183

Characteristics

Processing

Additive Manufacturing

Delivery form

Monofilament

Special Characteristics

Transparent

Certifications

Food contact

Regional Availability

Europe