

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at 100% elongation	2.6	MPa	ISO 527
Tensile Strength	5.2	MPa	ISO 37
Strain at break	600	%	ISO 37
Tear strength	28	kN/m	ISO 34-1
Shore A hardness	70	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	870	kg/m ³	ISO 1183
Biobased content	34	%	-

Characteristics**Features**

Good Adhesion, Soft Feel

Certifications

Contains renewable resources

Applications

Automotive, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific