

LAPRENE® 8K1901A60 NERO

TPS

Celanese

| Mechanical properties | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ISO Data | | | |
| ^[C] Stress at 100% elongation | 2.3 | MPa | ISO 527 |
| ^[C] Stress at 300% elongation | 4.6 | MPa | ISO 527 |
| ^[C] Shore A hardness | 62 | - | ISO 7619-1 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| ^[C] Density | 1040 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics**Delivery form**

Black