

LAPRENE® 8M35..D40

TPS

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	6.7	MPa	ISO 527
^[C] Stress at 300% elongation	8	MPa	ISO 527

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	980	kg/m ³	ISO 1183

[C]: CAMPUS