

LAPRENE® 8MFD..A65

TPS

Celanese

| Mechanical properties | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ISO Data | | | |
| ^[C] Stress at 100% elongation | 2 | MPa | ISO 527 |
| ^[C] Stress at 300% elongation | 2.9 | MPa | ISO 527 |
| ^[C] Shore A hardness | 66 | - | ISO 7619-1 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| ^[C] Density | 968 | kg/m ³ | ISO 1183 |

[C]: CAMPUS