

| Mechanical properties                        | Value | Unit | Test Standard |
|--|-------|------|---------------|
| <b>ISO Data</b>                              |       |      |               |
| <sup>[C]</sup> Stress at 100% elongation     | 3.5   | MPa  | ISO 527       |
| <sup>[C]</sup> Stress at 300% elongation     | 4.5   | MPa  | ISO 527       |
| <sup>[C]</sup> Compression set at 70 °C, 24h | 50    | %    | ISO 815       |
| <sup>[C]</sup> Shore A hardness              | 88    | -    | ISO 7619-1    |

[C]: CAMPUS

| Other properties       | Value | Unit              | Test Standard |
|------------------------|-------|-------------------|---------------|
| <sup>[C]</sup> Density | 1190  | kg/m <sup>3</sup> | ISO 1183      |

[C]: CAMPUS

## Characteristics

### Delivery form

Natural Color