

| Mechanical properties | Value | Unit | Test Standard |
|--|-------|------|---------------|
| ISO Data | | | |
| ^[C] Stress at 100% elongation | 2.2 | MPa | ISO 527 |
| ^[C] Stress at 300% elongation | 3 | MPa | ISO 527 |
| ^[C] Compression set at 70 °C, 24h | 55 | % | ISO 815 |
| ^[C] Shore A hardness | 73 | - | ISO 7619-1 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|------------------------|-------|-------------------|---------------|
| ^[C] Density | 1170 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics

Delivery form

Natural Color