

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	1.9	MPa	ISO 527
^[C] Stress at 300% elongation	2.8	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	38	%	ISO 815
^[C] Shore A hardness	66	-	ISO 7619-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1170	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Black