

**LAPRENE® 830000696ED NEUTRO**

TPS

Celanese

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Stress at 100% elongation	<b>1.8</b>	MPa	ISO 527
<sup>[C]</sup> Stress at 300% elongation	<b>3.6</b>	MPa	ISO 527
<sup>[C]</sup> Shore A hardness	<b>59</b>	-	ISO 7619-1

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1090</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

U.V. stabilized or stable to weather

**Delivery form**

Pellets, Natural Color

**Regional Availability**

North America, South and Central America