

| Mechanical properties | Value | Unit | Test Standard |
|--|------------|------|---------------|
| ISO Data | | | |
| ^[C] Stress at 100% elongation | 2.8 | MPa | ISO 527 |
| ^[C] Stress at 300% elongation | 3.8 | MPa | ISO 527 |
| ^[C] Compression set at 70 °C, 24h | 53 | % | ISO 815 |
| ^[C] Shore A hardness | 82 | - | ISO 7619-1 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|------------------------|-------------|-------------------|---------------|
| ^[C] Density | 1040 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics

Delivery form

Black