

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Abrasion resistance	90	mm ³	ISO 4649
ASTM Data			
Tensile Strength	14	MPa	ASTM D 638
Elongation at Break	600	%	ASTM D 638
Modulus at 100% Elongation	3.5	MPa	ASTM D 412
Modulus at 300% Elongation	6	MPa	ASTM D 412
Shore A Hardness	80	-	ASTM D 2240
Tear Strength	50	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ASTM D 792

Characteristics

Processing
Injection Molding, Other Extrusion

Chemical Resistance
Oil Resistance

Features
Soft Feel

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa