

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Abrasion resistance	<b>40</b>	mm <sup>3</sup>	ISO 4649
<b>ASTM Data</b>			
Tensile Strength	<b>45</b>	MPa	ASTM D 638
Elongation at Break	<b>500</b>	%	ASTM D 638
Flexural Modulus	<b>250</b>	MPa	ASTM D 790
Shore D Hardness	<b>58</b>	-	ASTM D 2240
Tear Strength	<b>130</b>	kN/m	ASTM D 624
<b>Other properties</b>			
Biobased content	<b>25</b>	%	-
Density	<b>1160</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets

**Features**

Good Adhesion

**Certifications**

Contains renewable resources

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa