

**AVALON® 65 AB**

TPU

Huntsman Polymers Corp.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>30</b>	MPa	ISO 37
Strain at break	<b>700</b>	%	ISO 37
Tear strength	<b>40</b>	kN/m	ISO 34-1
Abrasion resistance	<b>60</b>	mm <sup>3</sup>	ISO 4649
Shore A hardness	<b>65</b>	-	ISO 7619-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1180</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	<b>160 - 200</b>	°C	-
Mold temperature	<b>25 - 45</b>	°C	-
Screw speed	<b>20 - 80</b>	rpm	-
Injection pressure	<b>40</b>	MPa	-
Back pressure	<b>0.3 - 3</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Features**

Scratch Resistant

**Chemical Resistance**

Hydrolytically Stable

**Applications**

Sports Equipment

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa