

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Flexural modulus, 23°C	1400	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	6.1	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	3	kJ/m <sup>2</sup>	ISO 179/1eA
Tensile Strength	40	MPa	ISO 37
Strain at break	60	%	ISO 37
Shore D hardness	75	-	ISO 7619-1
<b>Other Standards<sup>S1</sup></b>			
Stress at 10% elongation	45	MPa	DIN 53504

S: These properties are reported by the producer according standards that are different to our defaults.

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	89	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	95	°C	ISO 75-1/-2
Vicat softening temperature, A	113	°C	ISO 306
Vicat softening temperature, B	99	°C	ISO 306

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	90 - 100	°C	-
Melt temperature	230 - 250	°C	-
Mold temperature	45 - 55	°C	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	90 - 100	°C	-
Melt temperature	220 - 250	°C	-

## Characteristics

### Processing

Injection Molding, Other Extrusion

### Delivery form

Pellets

### Special Characteristics

Opaque, Translucent

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa