

EMI 1262 T-80A

TPU

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.01	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	6.21	MPa	ASTM D 638
Shore A Hardness	80	-	ASTM D 2240
Izod Impact notched, 1/8 in	107	J/m	ASTM D 256

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	10000	Ohm	ASTM D 257
Volume Resistivity	100	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1180	kg/m ³	ASTM D 792
Moisture Content	0.01	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	107	°C	-
Pre-drying - Time	6	h	-
Melt temperature	185 - 218	°C	-
Mold temperature	37.8 - 60	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Features

EMI Attenuation/Shielding