

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>39</b>	MPa	ASTM D 638
Elongation at Break	<b>680</b>	%	ASTM D 638
Modulus at 100% Elongation	<b>4.6</b>	MPa	ASTM D 412
Modulus at 300% Elongation	<b>7.1</b>	MPa	ASTM D 412
Shore A Hardness	<b>82</b>	-	ASTM D 2240
Tear Strength	<b>43.9</b>	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	<b>28</b>	%	ASTM D 395
Compression Set , 22 hr @ 158 °F	<b>71</b>	%	ASTM D 395

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1110</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Regional Availability**

North America, Europe, Asia Pacific