

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	6.21	MPa	ASTM D 412
Modulus at 300% Elongation	4.6	MPa	ASTM D 412
Shore A Hardness	90	-	ASTM D 2240
Tear Strength	78.8	kN/m	ASTM D 624

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	144	°C	ASTM D 3418
Glass Transition Temperature	-23.9	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ASTM D 792

Characteristics**Processing**

Blown Film Extrusion, Film Extrusion

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets