

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	6.89	MPa	ASTM D 412
Modulus at 300% Elongation	2.53	MPa	ASTM D 412
Shore A Hardness	90	-	ASTM D 2240
Tear Strength	57.8	kN/m	ASTM D 624

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Limiting Oxygen Index	28	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ASTM D 792

Characteristics

Processing

Wire/Cable Extrusion, Other Extrusion

Delivery form

Pellets

Special Characteristics

Flame retardant

Chemical Resistance

General Chemical Resistance, Oil Resistance

Regional Availability

North America, Europe, Asia Pacific