

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	4.48	MPa	ASTM D 412
Modulus at 300% Elongation	2.76	MPa	ASTM D 412
Shore A Hardness	80	-	ASTM D 2240
Tear Strength	61.3	kN/m	ASTM D 624

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	135	°C	ASTM D 3418
Glass Transition Temperature	-37.2	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	1210	kg/m ³	ASTM D 792

Characteristics

Processing

Blown Film Extrusion, Film Extrusion

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets