

**Estane® 58284 TPU**

TPU

Lubrizol Advanced Materials Spain S.L.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Modulus at 100% Elongation	<b>6.55</b>	MPa	ASTM D 412
Modulus at 300% Elongation	<b>4.36</b>	MPa	ASTM D 412
Shore A Hardness	<b>85</b>	-	ASTM D 2240
Tear Strength	<b>77</b>	kN/m	ASTM D 624

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Glass Transition Temperature	<b>-43.9</b>	°C	ASTM E 1356

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1100</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Wire/Cable Extrusion

**Delivery form**

Pellets

**Chemical Resistance**

General Chemical Resistance, Oil Resistance

**Applications**

General Purpose

**Regional Availability**

North America, Europe, Asia Pacific