

Estane® ALR CL87A-V TPU

TPU

Lubrizol Advanced Materials Spain S.L.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5	g/10min	ASTM D 1238
Temperature	175	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	21.37	MPa	ASTM D 790
Modulus at 100% Elongation	6.89	MPa	ASTM D 412
Shore A Hardness	87	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America, Europe, Asia Pacific