

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	14.5	MPa	ASTM D 412
Modulus at 300% Elongation	11	MPa	ASTM D 412
Shore D Hardness	55	-	ASTM D 2240
Tear Strength	154	kN/m	ASTM D 624

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	180	°C	ASTM D 3418
Glass Transition Temperature	-38.9	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	1230	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Pipe/Tube Extrusion, Profile Extrusion

Delivery form

Pellets

Special Characteristics

Transparent

Chemical Resistance

General Chemical Resistance

Regional Availability

North America, Europe, Asia Pacific