

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	20.7	MPa	ASTM D 412
Modulus at 300% Elongation	14.7	MPa	ASTM D 412
Shore D Hardness	60	-	ASTM D 2240
Tear Strength	158	kN/m	ASTM D 624
Thermal properties			
ASTM Data			
Melting Temperature	161	°C	ASTM D 3418
Glass Transition Temperature	-18.3	°C	ASTM E 1356
Other properties			
Density	1170	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Pipe/Tube Extrusion, Profile Extrusion, Wire/Cable Extrusion

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather, Transparent

Regional Availability

North America, Europe, Asia Pacific