

Estane® GP 65DE TPU

TPU

Lubrizol Advanced Materials Spain S.L.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	249	MPa	ISO 527
Stress at 100% elongation	25	MPa	ISO 527
Stress at 300% elongation	32	MPa	ISO 527
Stress at break TPE	49	MPa	ISO 527
Strain at break TPE	>300	%	ISO 527
Compression set at 23 °C, 24h	18	%	ISO 815
Compression set at 70 °C, 24h	24	%	ISO 815
Tear strength	225	kN/m	ISO 34-1
Abrasion resistance	42	mm ³	ISO 4649
Shore D hardness	65	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, A	152	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1260	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets