

Gravi-Tech™ GRV-UR-075-W-BLK

TPU

Avient Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0075	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	317	MPa	ASTM D 790
Shore D Hardness	55	-	ASTM D 2240
Izod Impact notched, 1/8 in	330	J/m	ASTM D 256
Elongation at Break	80	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	7500	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Applications

Medical, Sports Equipment

Regional Availability

North America