

ISOTHANE 1160D

TPU

Great Eastern Resins Industrial Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	19	MPa	ASTM D 412
Modulus at 300% Elongation	33	MPa	ASTM D 412
Shore D Hardness	58	-	ASTM D 2240
Tear Strength	200	kN/m	ASTM D 624
Tensile Strength	40	MPa	ASTM D 412
Elongation at Break	480	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1210	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Special Characteristics

Transparent

Chemical Resistance

Solvent Resistance

Applications

Electrical and Electronical, General Purpose, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa