

ISOTHANE 1680AE

TPU

Great Eastern Resins Industrial Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 300% Elongation	7.5	MPa	ASTM D 412
Shore A Hardness	80	-	ASTM D 2240
Tear Strength	7.8	kN/m	ASTM D 624
Tensile Strength	18	MPa	ASTM D 412
Elongation at Break	848	%	ASTM D 412

Characteristics**Processing**

Other Extrusion, Blow Molding

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa