

ISOTHANE 3090A

TPU

Great Eastern Resins Industrial Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	10	MPa	ASTM D 412
Modulus at 300% Elongation	21	MPa	ASTM D 412
Shore A Hardness	90	-	ASTM D 2240
Tear Strength	750	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	25	%	ASTM D 395
Compression Set , 22 hr @ 158 °F	30	%	ASTM D 395
Tensile Strength	39	MPa	ASTM D 412
Elongation at Break	480	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1140	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion, Blow Molding

Features

Fungus Resistance

Chemical Resistance

Hydrolytically Stable

Applications

General Purpose, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa