

ISOTHANE 5075A

TPU

Great Eastern Resins Industrial Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	3.2	MPa	ASTM D 412
Modulus at 300% Elongation	5.9	MPa	ASTM D 412
Shore A Hardness	75	-	ASTM D 2240
Tear Strength	400	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	25	%	ASTM D 395
Compression Set , 22 hr @ 158 °F	35	%	ASTM D 395
Tensile Strength	31	MPa	ASTM D 412
Elongation at Break	650	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion, Blow Molding

Features

Fungus Resistance

Chemical Resistance

Hydrolytically Stable

Applications

Medical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa