

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Charpy notched impact strength, +23°C	<b>100</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	<b>100</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Stress at 100% elongation	<b>1.5</b>	MPa	ISO 527
Stress at 300% elongation	<b>2</b>	MPa	ISO 527
Stress at break TPE	<b>35</b>	MPa	ISO 527
Strain at break TPE	<b>1000</b>	%	ISO 527
Compression set at 23 °C, 24h	<b>25</b>	%	ISO 815
Compression set at 70 °C, 24h	<b>42</b>	%	ISO 815
Compression set at 100 °C, 24h	<b>58</b>	%	ISO 815
Shore A hardness	<b>63</b>	-	ISO 7619-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1170</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Delivery form**

Natural Color

**Applications**

Automotive, Encapsulation

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

Europe

**Features**

Tribologic Grade