

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Charpy notched impact strength, +23°C	100	kJ/m ²	ISO 179/1eA
Stress at break TPE	50	MPa	ISO 527
Strain at break TPE	650	%	ISO 527
Shore A hardness	85	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1180	kg/m ³	ISO 1183

Characteristics

Processing
Injection Molding

Features
Tribologic Grade

Delivery form
Natural Color

Applications
Automotive, Encapsulation

Special Characteristics
U.V. stabilized or stable to weather

Regional Availability
Europe