

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Charpy notched impact strength, +23°C	100	kJ/m <sup>2</sup>	ISO 179/1eA
Stress at break TPE	45	MPa	ISO 527
Strain at break TPE	750	%	ISO 527
Compression set at 70 °C, 24h	20	%	ISO 815
Compression set at 100 °C, 24h	30	%	ISO 815
Shore A hardness	85	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1200	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Delivery form**

Natural Color

**Applications**

Automotive, Encapsulation

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

Europe

**Features**

Tribologic Grade