

MIRATHANE® E195L

TPU

Miracell Chemicals Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	15	MPa	ASTM D 412
Modulus at 300% Elongation	25	MPa	ASTM D 412
Shore A Hardness	95	-	ASTM D 2240
Tear Strength	130	kN/m	ASTM D 624
Tensile Strength	45	MPa	ASTM D 412
Elongation at Break	500	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Glass Transition Temperature	-25	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Characteristics**Processing**

Wire/Cable Extrusion

Applications

Electrical and Electronical

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America, Europe, Asia Pacific