

MIRATHANE® E375

TPU

Miracell Chemicals Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	4	MPa	ASTM D 412
Modulus at 300% Elongation	8	MPa	ASTM D 412
Shore A Hardness	78	-	ASTM D 2240
Tear Strength	100	kN/m	ASTM D 624
Tensile Strength	30	MPa	ASTM D 412
Elongation at Break	600	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Glass Transition Temperature	-30	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Platable, Transparent

Regional Availability

North America, Europe, Asia Pacific