

MIRATHANE® E375D

TPU

Miracell Chemicals Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	26	MPa	ASTM D 412
Modulus at 300% Elongation	28	MPa	ASTM D 412
Shore D Hardness	75	-	ASTM D 2240
Tear Strength	240	kN/m	ASTM D 624
Tensile Strength	50	MPa	ASTM D 412
Elongation at Break	300	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Glass Transition Temperature	-5	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Platable, Transparent

Regional Availability

North America, Europe, Asia Pacific