

MIRATHANE® F620

TPU

Miracell Chemicals Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tear Strength	15	kN/m	ASTM D 624
Tensile Strength	1.3	MPa	ASTM D 412
Elongation at Break	170	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	2300	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

U.V. stabilized or stable to weather

Features

Anti Slip

Chemical Resistance

General Chemical Resistance

Applications

Automotive, Packaging

Regional Availability

North America, Europe, Asia Pacific