

MIRATHANE® G365

TPU

Miracell Chemicals Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	2	MPa	ASTM D 412
Modulus at 300% Elongation	4	MPa	ASTM D 412
Shore A Hardness	67	-	ASTM D 2240
Tear Strength	65	kN/m	ASTM D 624
Tensile Strength	20	MPa	ASTM D 412
Elongation at Break	700	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Glass Transition Temperature	-43	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Transparent

Regional Availability

North America, Europe, Asia Pacific

Applications

Electrical and Electrical