

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[5]			
Melt Flow Index, MFI	2	g/10min	
Temperature	190	°C	-
Load	8.7	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
Other Standards^[5]			
Modulus at 100% Elongation	1.28	MPa	
Tensile Strength at Break	6.83	MPa	
Elongation at Break	501	%	

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Other Standards^[5]			
Density	960	kg/m ³	

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Delivery form

Natural Color

Regional Availability

North America

Certifications

Medical Grade, US Pharmacopeia Class VI Approved