

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Melt Flow Index, MFI	<b>4</b>	g/10min	
Temperature	<b>190</b>	°C	-
Load	<b>8.7</b>	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Modulus at 100% Elongation	<b>1.77</b>	MPa	
Tensile Strength at Break	<b>9.43</b>	MPa	
Elongation at Break	<b>575</b>	%	

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Density	<b>980</b>	kg/m <sup>3</sup>	

S: These properties are reported by the producer according standards that are different to our defaults.

### Characteristics

#### Delivery form

Natural Color

#### Regional Availability

North America

#### Certifications

Medical Grade, US Pharmacopeia Class VI Approved