

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[S]			
Melt Flow Index, MFI	13	g/10min	
Temperature	190	°C	-
Load	8.7	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
Other Standards^[S]			
Modulus at 100% Elongation	4.1	MPa	
Tensile Strength at Break	17.3	MPa	
Elongation at Break	542	%	

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Other Standards^[S]			
Density	1040	kg/m ³	

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Delivery form

Natural Color

Regional Availability

North America

Certifications

Medical Grade, US Pharmacopeia Class VI Approved