

NEVIEL 460D

TPU

Nevicolor S.p.A.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	35	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	77	MPa	ISO 178
Izod notched impact strength, +23°C	N	kJ/m ²	ISO 180/1A
Shore D hardness	46	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, A	78	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1270	kg/m ³	ISO 1183

Characteristics**Delivery form**

Black

Regional Availability

Europe

Special Characteristics

Increased electrical conductivity