

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Strain at break	630	%	ISO 37
Compression set at 70 °C, 24h	80	%	ISO 815
Shore A hardness	55	-	ISO 7619-1
Other properties			
Density	1020	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	2	h	-
Melt temperature	170 - 210	°C	-
Mold temperature	30 - 60	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Features

Scratch Resistant

Chemical Resistance

General Chemical Resistance, Oil Resistance

Applications

Automotive, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa