

OnFlex™ U 5365A-E0134 FG

TPU

Avient Corporation

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Strain at break	620	%	ISO 37
Shore A hardness	65	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1090	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	2	h	-
Melt temperature	170 - 210	°C	-
Mold temperature	30 - 60	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa