

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Strain at break	580	%	ISO 37
Tear strength	53	kN/m	ISO 34-1
Shore A hardness	70	-	ISO 7619-1

Optical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Gloss, 60°	6	-	ISO 2813

Other properties	Value	Unit	Test Standard
Density	1080	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	2	h	-
Melt temperature	170 - 210	°C	-
Mold temperature	30 - 60	°C	-

## Characteristics

### Processing

Injection Molding, Film Extrusion, Calendering

### Delivery form

Pellets

### Features

Scratch Resistant

### Chemical Resistance

General Chemical Resistance, Oil Resistance

### Applications

Automotive, General Purpose

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa