

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Strain at break	490	%	ISO 37
Tear strength	59	kN/m	ISO 34-1
Shore A hardness	70	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	2	h	-
Melt temperature	160 - 200	°C	-
Mold temperature	30 - 60	°C	-

Characteristics

Processing

Injection Molding, Film Extrusion, Calendering

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather

Features

Scratch Resistant

Chemical Resistance

General Chemical Resistance, Oil Resistance

Applications

Automotive, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa