

**Pearlstick™ 5778**

TPU

Lubrizol Advanced Materials Spain S.L.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>34.5</b>	MPa	ASTM D 638
Elongation at Break	<b>250</b>	%	ASTM D 638
Modulus at 100% Elongation	<b>17.9</b>	MPa	ASTM D 412
Shore D Hardness	<b>78</b>	-	ASTM D 2240

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Glass Transition Temperature	<b>31</b>	°C	ASTM E 1356
Vicat Temperature	<b>38</b>	°C	ASTM D 1525

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1210</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Calendering

**Delivery form**

Pellets

**Features**

Blending Resin, Good Adhesion

**Chemical Resistance**

Hydrolytically Stable

**Regional Availability**

North America, Europe, Asia Pacific