

**Product Texts**

Polycaprolactone copolyester-based TPU.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>39</b>	MPa	ISO 527
Stress at 50% strain	<b>7</b>	MPa	ISO 527
Stress at 100% elongation	<b>8</b>	MPa	ISO 527
Stress at 300% elongation	<b>17</b>	MPa	ISO 527
Strain at break TPE	<b>500</b>	%	ISO 527
Tear strength	<b>112</b>	kN/m	ISO 34-1
Abrasion resistance	<b>30</b>	mm <sup>3</sup>	ISO 4649
Shore A hardness	<b>91</b>	-	ISO 7619-1

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Vicat softening temperature, A	<b>96</b>	°C	ISO 306

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1200</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Extrusion</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>100</b>	°C	-
Pre-drying - Time	<b>3 - 4</b>	h	-
Zone 1	<b>200</b>	°C	-
Zone 2	<b>210</b>	°C	-
Zone 3	<b>215</b>	°C	-
Zone 4	<b>220</b>	°C	-
Nozzle temperature	<b>210</b>	°C	-

**Characteristics**

**Processing**

Other Extrusion

**Regional Availability**

North America, Europe